(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property **Organization** International Bureau



13 JAN 2005

(43) International Publication Date 19 February 2004 (19.02.2004)

PCT

(10) International Publication Number WO 2004/014978 A1

(51) International Patent Classification7: 18/67, C09D 175/16, C08J 7/04

C08G 18/42,

(74) Agent: NAPOLI, James, J.; Marshall, Gerstein & Borun LLP, 233 S. Wacker Drive, Suite 6300, Sears Tower, Chicago, IL 60606-6357 (US).

(21) International Application Number:

PCT/US2003/022722

(22) International Filing Date: 21 July 2003 (21.07.2003)

(25) Filing Language:

English

(26) Publication Language:

(30) Priority Data:

60/402,657 60/431,811

12 August 2002 (12.08.2002) US 9 December 2002 (09.12.2002) US

English

(71) Applicant (for all designated States except US): VALSPAR SOURCING, INC. [US/US]; 1101 South Third Street, Minneapolis, MN 55415 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): GARNER, Archie, Wayne [US/US]; 452 148 Avenue NE, Ham Lake, MN 55304 (US). ROBERTSON, Brian, Allan [CA/CA]; 74 Columbia Avenue, RR #1, Long Sault, Ontario K0C 1P0 (CA). MELNYK, Thomas, John [US/US]; 10645 Greenfield Road, Greenfield, MN 55357 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,

LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,

MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,

SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: URETHANE ACRYLATE GEL COAT RESIN AND METHOD OF MAKING

(57) Abstract: An improved urethane acrylate gel coat resin, its method of manufacture, and its use in gel coat compositions are disclosed. The urethane acrylate gel coat resin contains terminal acrylate moieties and is the reaction product of an oligoester of weight average molecular weight about 200 to about 4000, a diisocyanate, and a hydroxyalkyl (meth)acrylate. The gel coat resin is used in gel coat compositions that exhibit good weatherability and color stability after cure.